



ECOSTICK® PRIMER M

Description/Nature of the product

Acqueous dispersion of a polymer based on polyurethane modified, ca.35%

Application by

Spray gun, brush

Characteristics

Bandaging and coupling of metal with leather and textiles

Instructions for use

PRIMER M can be mixed with HARTER FI 1002 A and applied on a metal surface within 4 hours; let it dry completely for at least one hour and couple within 3 days with leather or textile after applying ECOSTICK® 1816B on both sides. Couple when the product ECOSTICK® 1816B is still damp or within 20/30 minutes after the adhesive is dried. After this period, reactivate both sides at 60°C.

Open Time

3 days

Remarks

Shake PRIMER M before use



Intercom Srl ® - P.iva e C.F. 06183210480

Address: Via della Gora, 13 - 50025 Montespertoli - Firenze - Italia

Phone: +39 0571 671096 - **Fax:** +39 0571 671151 - **Email:** info@intercomsas.it - **Web:** www.intercomsas.it